

OVEREXPANDED FLEXIBLE POLYOLEFIN MARKER SLEEVES
FOR USE WITH SUMIMARK III & IV MARKING SYSTEMS
3 : 1 Shrink Ratio

UL RECOGNIZED 125°C 600V (VW-1)



RoHS Compliant

TYPICAL FEATURES	
<p>1) SUMIMARK SM3 - 23 tubing is a very flexible, flame retarded, heat-shrinkable polyolefin tubing that is recognized by Underwriters' Laboratories (UL) Subject 224 as 125°C, 600V (VW-1) rated. SM23 has a 3 to 1 expansion ratio. SUMIMARK SM3 - 23 meets the material requirements of AMS-DTL-23053 / 5, Classes 1 & 3. Sumimark SM3-23 is <i>not</i> compatible with earlier Model 1 and 2 Sumimark systems.</p> <p>2) SUMIMARK SM3 - 23 tubing, when used in conjunction with the SUMIMARK III or IV Marking Systems, produces marked sleeves that meet or exceed the print permanence requirements of SAE-AS81531. Sumimark SM3 - 23 tubing is <i>not</i> compatible with earlier Model I and Model 2 Sumimark Systems.</p> <p>3) Shrink temperature is 90°C.</p>	<p>4) Operating temperature range is -55°C to +135°C and up to 200°C for short durations.</p> <p>5) SM3 - 23 is recommended for use in general purpose applications such as wire marking, identification and electrical insulation of light wire harness assemblies. It can also provide the user with better economies, as one size tubing can often replace two standard 2:1 expanded tubing sizes, thereby reducing inventories.</p>

STANDARD SIZES						
SIZE	INSIDE DIAMETER AS SUPPLIED (MIN)		INSIDE DIAMETER AFTER RECOVERY (MAX)		WALL THICKNESS AFTER RECOVERY (NOM)	
	INCH	(MM)	INCH	(MM)	INCH	(MM)
1/16	.063	(1.6)	.021	(0.5)	.020	(.50)
1/8	.125	(3.2)	.043	(1.1)	.024	(.60)
3/16	.188	(4.8)	.063	(1.6)	.026	(.65)
1/4	.250	(6.4)	.083	(2.1)	.028	(.70)
3/8	.375	(9.5)	.122	(3.1)	.031	(.80)
1/2	.500	(12.7)	.165	(4.2)	.033	(.85)
3/4	.750	(19.1)	.248	(6.3)	.039	(1.0)
1	1.000	(25.4)	.327	(8.3)	.048	(1.2)
1 1/2	1.500	(38.1)	.500	(12.7)	.050	(1.3)

Standard Colors: Black, white, yellow (Other colors available per factory acceptance and quote)
Standard Package: Spooled (S)
How to Order: (Type of material) (Size) (Color) (Packaging)
Example: SM3 - 23 1/4 White S

SM3 - 23 SPECIFICATION VALUES

PROPERTY (UNITS)	TEST METHOD	REQUIREMENT
Physical: Tensile strength (psi) Elongation (%) Specific gravity Low temperature flex (-55 ^o C) Heat shock (250 ^o C, 4 hrs.) Heat resistance (175 ^o C, 168 hrs.) Elongation (%) Secant modulus (psi) Longitudinal change (%)	ASTM D638 ASTM D638 ASTM D792 AMS-DTL-23053 AMS-DTL-23053 ASTM D638 ASTM D882 AMS-DTL-23053	1500 min. 200 min. 1.35 max. no cracking no cracking 100 min. 2.5 X 10 ⁴ max. +5, -15
Electrical: Dielectric strength (volts/mil) Volume resistivity (ohm-cm)	ASTM D876 ASTM D876	500 min. 1.0 X 10 ¹⁴ min.
Mark Permanence: Abrasion Fluid Resistance Isopropyl Alcohol/Mineral Spirits Terpene Defluxer H ₂ O/PGME/Monoethanolamine	SAE-AS81531 MIL-STD-202G Method 215J	20 rubs 10 rubs (x3) 10 rubs (x3) 10 rubs (x3)
Chemical: Corrosion (175 ^o C, 16 hrs.) Water absorption (%) Fluid resistance (23 ^o C, 24 hrs.) Tensile strength (psi) Flammability Shrink temperature, nominal	AMS-DTL-23053 ASTM D570 AMS-DTL-23053 UL 224 VW-1	no corrosion 0.5 max. 1000 min. pass 90 ^o C

Specification reference: SAE-AS81531
 UL-224 125^o C, 600V, VW-1
 File E48762 YDPU2
 CSA


SUMITOMO ELECTRIC
INTERCONNECT PRODUCTS INC.
www.seipusa.com

915 Armorlite Drive
 San Marcos, CA 92069

Telephone: (800) 758-3515
 FAX: (800) 758-3517

Rev. 08/31/10