

FLEXIBLE POLYVINYL CHLORIDE

2 : 1 Shrink Ratio

UL RECOGNIZED 105° C 600V (VW-1)



RoHS Compliant

TYPICAL FEATURES

- 1) SUMITUBE V is a flexible, flame retarded, radiation cross-linked heat-shrinkable PVC tubing recognized by Underwriters' Laboratories (UL) Subject 224 and rated VW-1.
- 2) SUMITUBE V has excellent flame-retardant properties with improved heat resistance and storage stability compared to conventional non-irradiated PVC.
- 3) Shrink temperature is 170° C.
- 4) Operating temperature range is -20° C to +105° C.

STANDARD SIZES

SIZE	INSIDE DIAMETER AS SUPPLIED (MIN)		INSIDE DIAMETER AFTER RECOVERY (MAX)		WALL THICKNESS AFTER RECOVERY (NOM)	
	INCH	(MM)	INCH	(MM)	INCH	(MM)
3/64	.046	1.2	.023	0.6	.020	0.51
1/16	.063	1.6	.031	0.8	.020	0.51
3/32	.093	2.4	.046	1.2	.025	0.64
1/8	.125	3.2	.062	1.6	.025	0.64
3/16	.187	4.8	.093	2.4	.025	0.64
1/4	.250	6.4	.125	3.2	.025	0.64
3/8	.375	9.5	.187	4.8	.025	0.64
1/2	.500	12.7	.250	6.4	.025	0.64
3/4	.750	19.1	.375	9.5	.030	0.76
1	1.000	25.4	.500	12.7	.035	0.89

Standard Colors: Black

Standard Package: Spooled (S)

How to Order: (Type of material) (Size) (Color) (Packaging)

Example: V 1/4 Black S

V SPECIFICATION VALUES

PROPERTY (UNITS)	TEST METHOD	REQUIREMENT
Physical: Tensile strength (psi) Elongation (%) Specific gravity Low temperature flex. (-10° C) Heat shock (121° C 1 Hr.) Heat resistance (136° C 168 Hrs.) Elongation (%) Secant modulus (psi) Deformation (125° C 1 Hr.) (%)	ASTM D638 ASTM D638 ASTM D792 UL 224 UL 224 ASTM D638 ASTM D882 UL 224	1500 MIN. 100 MIN. 1.35 MAX. No cracking No cracking 70% of unaged value MIN. 25000 MAX. 50 MAX.
Electrical: Dielectric withstand Volume resistivity (ohm-cm)	UL 224 ASTM D876	2500 MIN. 1.0 X 10 ¹⁰ MIN.
Chemical: Corrosion Copper stability (136° C 168 Hrs.) Elongation (%) Water absorption (%) Flammability Shrink temperature, nominal	UL 224 UL 224 ASTM D570 UL-224 VW-1	No corrosion 70% of unaged value MIN. 0.5 MAX. pass 170° C

Specification reference: UL-224 105° C, 600V, VW-1
 File E48762 YDPU2, Cat. No. 809

Marking: SUMITUBE V is surface printed with recognized UL marking as follows:
 "SUMITOMO-K CSA HS PVC TUBING 105° C OFT SUMITUBE V CAT 819 VW-1-F"



915 Armorlite Drive
 San Marcos, CA 92069

Telephone: (800) 758-3515
 FAX: (800) 758-3517